

PRODUCT LIST Technical Data Sheet 08/2009

automotive films		reference number	finish hardcoat	thick-ness [μ]	light transmission %	total solar transmission %	total solar rejection %	total solar energy absorbed %	solar energy rejected %	visible light rejection %	UV-rejection %	ABG-Nr.
Supreme Bond												
SL® automotive film	Supreme Bond 05	38800	sr	50	5	37	10	53	50	8	99	D5475
SL® automotive film	Supreme Bond 19	38810	sr	50	19	40	9	51	47	8	99	D5475
SL® automotive film	Supreme Bond 34	38815	sr	50	34	48	8	44	41	8	99	D5475
SL® automotive film	Supreme Bond 43	38820	sr	50	43	52	8	40	38	8	99	D5475
Royal Bond												
SL® automotive film	Royal Bond 05	38830	sr	50	5	24	12	64	60	10	99	D5474
SL® automotive film	Royal Bond 19	38840	sr	50	19	33	13	54	53	10	99	D5473
SL® automotive film	Royal Bond 34	38850	sr	50	34	42	11	47	46	11	99	D5473
SL® automotive film	Royal Bond 49	38860	sr	50	49	46	12	42	43	11	99	D5473
Pure Bond												
SL® automotive film	Pure Bond 05	38870	sr	50	4	42	8	50	45	8	99	D5495
SL® automotive film	Pure Bond 19	38880	sr	50	19	47	8	45	41	8	99	D5495
SL® automotive film	Pure Bond 34	38890	sr	50	34	50	8	42	39	8	99	D5495
Specials												
SL® automotive film	Alu Bond 05	38400	sr	60	5	13	31	56	71	13	99	D5317
SL® automotive film	Alu Bond 20	38160	sr	50	20	27	20	53	47	9	99	D5146
SL® automotive film	Chrome Bond 20	38120	sr	50	20	28	26	46	59	24	99	D5146
SL® automotive film	Mirror Bond 03	38125	sr	50	3	20	22	58	66	22	99	D5530
SL® automotive film	Spectra Bond/Neutral 70NR sr	38030	sr	50	70	49	27	24	45	15	99	D5531
SL® automotive film	Secure Bond 100	38900	sr	115	89	81	9	10	16	8	99	D5532
SL® automotive film	Secure Bond 175	38910	sr	190	88	81	9	10	18	8	99	D5532

minimum order quantity each film type 5m
all incoming OPALFILM® and SL® orders received until 3 PM (Fridays 12 PM)
will be forwarded on the same day if in stock.

- deviations in the thickness due to manufacturing tolerances are possible