



PRODUCT LIST Technical Data Sheet 08/2009



Automotive Films		finish	thickness	reference number	light transmission	total solar transmission	total solar reflection	total solar energy absorbed	solar energy rejected	visible light reflection	UV rejection	ABG-Nr.
		hardcoat	[μ] approx.		%	%	%	%	%	%	%	
Supreme Bond												
Automotive film Supreme Bond 05	Supreme Bond 05	sr	50	38800	5	37	10	53	50	8	99	D5475
Automotive film Supreme Bond 19	Supreme Bond 19	sr	50	38810	19	40	9	51	47	8	99	D5475
Automotive film Supreme Bond 34	Supreme Bond 34	sr	50	38815	34	48	8	44	41	8	99	D5475
Automotive film Supreme Bond 43	Supreme Bond 43	sr	50	38820	43	52	8	40	38	8	99	D5475
Royal Bond												
Automotive film Royal Bond 05	Royal Bond 05	sr	50	38830	5	24	12	64	60	10	99	D5474
Automotive film Royal Bond 19	Royal Bond 19	sr	50	38840	19	33	13	54	53	10	99	D5473
Automotive film Royal Bond 34	Royal Bond 34	sr	50	38850	36	42	11	47	46	11	99	D5474
Automotive film Royal Bond 49	Royal Bond 49	sr	50	38860	49	46	12	42	43	11	99	D5475
Pure Bond												
Automotive film Pure Bond 05	Pure Bond 05	sr	50	38870	4	42	8	50	45	8	99	D5495
Automotive film Pure Bond 19	Pure Bond 19	sr	50	38880	19	47	8	45	41	8	99	D5496
Automotive film Pure Bond 34	Pure Bond 34	sr	50	38890	34	50	8	42	39	8	99	D5495
Specials												
Automotive film Alu Bond 05	Alu Bond 05	sr	60	38400	5	13	31	56	71	13	99	pending
Automotive film Alu Bond 20	Alu Bond 20	sr	50	38160	20	27	20	53	47	9	99	pending
Automotive film Chrome Bond 20	Chrome Bond 20	sr	50	38120	20	28	26	46	59	24	99	pending
Automotive film Mirror Bond 03	Mirror Bond 03	sr	50	38125	3	20	22	58	66	22	99	pending
Automotive film Neutral 70NR sr	Spectra Bond	sr	50	38030	70	49	27	24	45	15	99	pending
Automotive film Secure Bond 100	Secure Bond 100	sr	115	38900	89	81	9	10	16	8	99	pending
Automotive film Secure Bond 175	Secure Bond 175	sr	190	38910	88	81	9	10	18	8	99	pending
Basic Bond												
Automotive film	Basic Bond 05	sr	37	38750	6	40	7	53	47	8	99	no ABG
Automotive film	Basic Bond 20	sr	37	38760	20	53	7	40	38	8	99	no ABG
Automotive film	Basic Bond 35	sr	37	38770	32	57	7	36	34	8	99	no ABG
Automotive film	Basic Bond 50	sr	37	38780	52	62	7	31	30	7	99	no ABG

All data is subject to normal manufacturing tolerances. Technical modifications reserved.

HAVERKAMP GmbH - Zum Kaiserbusch 26-28 - D - 48165 Münster - Tel. 0251/6262-0 - Fax 0251/6262-124 - www.haverkamp.de - mail info@haverkamp.de